

ばね用ステンレス鋼帯・鋼板 仕様・公差表

厚さ (mm)	許容差 (mm)	硬 さ (HV)									
		SUS301				SUS304			SUS631		
		1/2H	3/4H	H	EH	1/2H	3/4H	H	1/2H	3/4H	H
0.10~0.15	±0.010	310~369	370~429	430~489	490以上	250~309	310~369	370以上	350~399	400~449	450以上
0.16~0.24	±0.012										
0.25~0.39	±0.015										
0.40~0.59	±0.020										
0.60~0.99	±0.025										
1.00~1.24	±0.030										
1.50	+0.025~0.050										
2.00	+0.030~0.070										

みがき特殊帯鋼・鋼板 仕様・公差表

厚さ (mm)	許容差 (mm)	硬 さ (HV)				
		SK5M(SK85)	S50CM	S55CM(SAE1055)	S60CM(SAE1060)	S65C(SAE1065)
0.20~0.24	±0.015	200以下	180以下	180以下	190以下	190以下
0.25~0.39	±0.020					
0.40~0.59	±0.025					
0.60~0.89	±0.030					
0.90~1.19	±0.040					
1.20~1.59	±0.050					
1.60~2.09	±0.055					
2.10~2.99	±0.065					
3.00~4.00	±0.080					
5.00	±0.120					

ベーナイト鋼帯

厚さ (mm)	許容差 (mm)	BT60
0.20	±0.010	390~430
0.30~0.40	±0.020	380~420
0.50~0.80	±0.025	
1.00	±0.040	
1.20~1.60	±0.050	